

【地寶】PVC 複合木紋/石紋地板

# HETEROGENEOUS VINYL FLOORING

SEMI 太格

YOUR IDEAL FLOORING SOLUTION

STONE · WOOD · DURABLE · MEDISTUDIO




STONE

地寶 | 354


● 地寶

● : 現貨 ⊗ : 期貨 [期貨最低訂製量1600m<sup>2</sup>]

耐磨層 : 0.5mm 


## SEMIFLOR

### STONE COLLECTION

 : 2.0mm x 2m x 20m



3534 | Stone ● 現貨



3541 | Stone ● 現貨




3553 | Stone ⊗ 期貨

● : 現貨 ⊗ : 期貨 [期貨最低訂製量1600m<sup>2</sup>]




32401 | Wood ● 現貨

耐磨層 : 0.5mm 

## SEMIFLOR

### WOOD COLLECTION

 : 2.0mm x 2m x 20m



32301 | Wood ● 現貨




32502 | Wood ● 現貨




32501 | Wood ● 現貨


# SEMIFLOR DURABLE · MEDISTUDIO

☞ : 2.0mm x 2m x 20m ● : 現貨 ⊗ : 期貨 [期貨最低訂製量1600m<sup>2</sup>]


耐磨層 : 0.7mm 



92006 | Durable ● 現貨



92007 | Durable ● 現貨




90094 | Durable ● 現貨



97777 | Durable ● 現貨



98086 | Durable ● 現貨



25707 | MediStudio ● 現貨



25708 | MediStudio ● 現貨



99911 | Durable ● 現貨



# 【地寶】PVC 複合木紋 / 石紋地板

SEMI 太格

## HETEROGENEOUS VINYL FLOORING

Stone, Wood, Durable & MediStudio are manufactured by LG Hausys Ltd.

For detailed installation and maintenance procedures, please contact Semiflor representative for further details.

[適用場所] 商場 · 辦公室 · 醫療院所 · 學校

Test Method / 測試方法	Property / 測試項目	Stone · Wood · Durable · MediStudio / 測試結果
Total thickness / 總厚度	EN 428	2.0 mm
Weight / 重量	EN 430	Durable / MediStudio: 3050 g/m <sup>2</sup> Stone / Wood : 3100 g/m <sup>2</sup>
Roll width / 卷材寬度	EN 426	2.0 m
Roll length / 卷材長度	-	20 m
Thickness of wear layer / 耐磨層厚度	EN 429	Durable / MediStudio: 0.7mm Stone / Wood: 0.5mm
Wear group / 耐磨等級	EN 660-2	T 級
Residual indentation / 殘存凹陷度	EN 433	<0.06mm
Dimensional stability / 尺寸穩定性	EN 434	<0.10 %
Castor chair sustainability / 腳輪耐磨性	EN 425	Fulfilled 適用
Color fastness to light / 顏色堅牢度	ISO 105 - B02	≥6級
Reaction to fire / 防焰性	EN 13501-1	Bfl-S1
Anti-bacterial / 抗菌性	ISO 22196	具抗菌效果
Slip resistance / 止滑性	DIN 51130	R9
Body voltage / 人體帶電壓	EN 1815	<2kV
Plasticizer / 塑化劑	CNS 15138-1	符合國家標準 < 0.1%

